



BPP200

BPP200 is formulated for Blow Molding, Thermoforming & Sheet Extrusion. It meets the requirements of the FDA regulation 21CFR.1520

Physical Property	Test Method	Typical Value
Melt Flow g/10 min.	D 1238	2.0
Tensile Strength, @ Yield (psi)	D 638	4000
Elongation @ Yield (%)	D 638	8.5
Flexural Modulus, (psi x 10 ³)	D 790	180000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	NB
Heat Deflection Temp. @ 66 psi,(F)	D 648	220

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringement of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.