



## **BPP400**

BPP400 is formulated for Blow Molding, Thermoforming & Sheet Extrusion. It meets the requirements of the FDA regulation 21CFR.1520

<b>Physical Property</b>	<b>Test Method</b>	<b>Typical Value</b>
Melt Flow g/10 min.	D 1238	4.0
Tensile Strength, @ Yield (psi)	D 638	4400
Elongation @ Yield (%)	D 638	8.0
Flexural Modulus, (psi x 10 <sup>3</sup> )	D 790	200000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	3.5
Heat Deflection Temp. @ 66 psi,(F)	D 648	220

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringement of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.