



PA66101

PA66101 is a general purpose nylon 66 polyamide resin suitable for injection molding and extrusion.

Physical Property	Test Method	Typical Value
Density (g/cc)	ISO 1183	1.14
Tensile Strength, @ Yield (psi)	ISO 527	11900
Elongation @ Yield (%)	ISO 527	4.5
Flexural Modulus, (psi)	ISO 178	410000
Heat Deflection Temp. @ 66 psi,(F)	ISO 75	392
Melting Temp.(F)	ISO 11357	504

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.