



## **PA6670GH**

PA6670GH is a glass filled, heat stabilized, moisture resistant polyamide 66 resin suitable for injection molding.

<b>Physical Property</b>	<b>Test Method</b>	<b>Typical Value</b>
Density (g/cc)	ISO 1183	1.32
Tensile Strength @ Break (psi)	ISO 527	26100
Strain @ Break (%)	ISO 527	3
Tensile Modulus, (psi )	ISO 178	1200000
Heat Deflection Temp. @ 66 psi,(F)	ISO 75	502
Melting Temp.(F)	ISO 11357	504

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.