



PP 2000NW

An antistated, controlled rheology polypropylene homopolymer produced using catalyst technology. PP2000 is designed for injection molding applications that require improved impact. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

Typical Applications:
Features and Options:
Description:

Physical Property	Test Method	Typical Value
Melt Flow g/10 min.	ASTM D 1238	20
Density g/cc	ASTM D 792	0.900
Tensile Strength, @Yield psi	ASTM D 638	4400
Tensile Strength, @Break psi	ASTM D 638	3700
Elongation @ Yield %	ASTM 638	15
Elongation @ Break %	ASTM D 638	500
Flexural Modulus, Tangent psi	ASTM D 790	240,000
TUP Impact in-lbf		80
Notched Izod Impact Strength ft-lbf/in	ASTM D 256	0.4

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.