



PP2000W

PP2000W is formulated with antistat for Injection Molding.
It meets the requirements of the FDA regulation 21CFR177.1520

Physical Property	Test Method	Typical Value
Melt Flow g/10 min.	D 1238	20.0
Tensile Strength, @ Yield (psi)	D 638	4400
Elongation @ Yield (%)	D 638	15.0
Flexural Modulus, (psi)	D 790	200000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	0.6
Heat Deflection Temp.@ 66 psi,(F)	D 648	210

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.