



PP 3000NW

A controlled rheology polypropylene homopolymer produced using Ziegler-Natta catalyst technology. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

Physical Property	Test Method	Typical Value
Melt Flow g/10 min.	ASTM D 1238	30
Density g/cc	ASTM D 792	0.900
Tensile Strength, @Yield psi	ASTM D 638	5000
Tensile Strength, @Break psi	ASTM D 638	2850
Elongation @ Yield %	ASTM 638	20
Elongation @ Break %	ASTM D 638	480
Flexural Modulus, Tangent psi	ASTM D 790	230,000
Tensile Modulus, psi	ASTM D 638	170,000
TUP Impact in-lbf		63
Notched Izod Impact Strength ft-lbf/in	ASTM D 256	0.4

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringement of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.