



PP 400

A polypropylene homopolymer produced utilizing unique catalyst technology for extrusion and compression molding end-uses. This material meets the Food and Drug Administration requirements of 21 CFR 177.1520.

Physical Property	Test Method	Typical Value
Melt Flow g/10 min.	ASTM D 1238	4
Tensile Strength, @Yield psi	ASTM D 638	5160
Tensile Elongation @ Yield %	ASTM D 638	7.4
Flexural Modulus, 1% Secant ¹ psi	ASTM D 790B	220,000
Notched Izod Impact Strength @23°C ft-lbs/in	ASTM D 256	1.3

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.