



## **LLD50926**

LLD50926 meets the requirements of the FDA regulation 21CFR 177.1520

Typical applications include trash cans, housewares ,lids etc.

<b>Physical Property</b>	<b>ASTM Test Method</b>	<b>Typical Value</b>
Melt Flow (g/10 min.)	D 1238	50
Density (g/cc)	D 1505	0.926
Tensile Strength, @ Yield (psi)	D 638	2100
Elongation @ Yield (%)	D 638	8.2
Flexural Modulus, (psi )	D 790	64000
Heat Deflection Temp. @ 66 psi,(F)	D 648	122

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.