



PC1500

PC1500 provides excellent toughness, heat deflection and optical clarity. It is FDA approved.

Physical Property	ASTM Test Method	Typical Value
Melt Flow (g/10 min.)	D 1238	15.0
Sp Gravity	D 792	1.20
Tensile Strength, @ Yield (psi)	D 638	8700
Elongation @ Break (%)	D 638	150
Flexural Modulus, (psi x 10 ³)	D 790	350000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	16.0
Heat Deflection Temp.@ 264 psi,(F)	D 648	260
Haze ,%	D1003	1

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.