



PMMA 1400

Physical Property	ASTM Test Method	Typical Value
Melt Flow (g/10 min.)	D 1238	14
Sp Gravity	D 792	1.07
Tensile Strength, @ Yield (psi)	D 638	6300 3.6
Elongation @ Yield (%)	D 638	
Flexural Modulus, (psi x 10 ³)	D 790	320000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	1.9
Heat Deflection Temp. @ 264 psi,(F)	D 648	186
Haze ,%	D1003	3.0

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.