



SAN300

SAN300 offers a balance of chemical resistance and physical properties. Applications include Houseware, Appliance etc.

Physical Property	ASTM Test Method	Typical Value
Melt Flow (g/10 min.)	D 1238	3.3
Sp Gravity	D 792	1.08
Tensile Strength, @ Yield (psi)	D 638	11300
Elongation @ Break (%)	D 638	2.9
Flexural Modulus, (psi x 10 ³)	D 790	560000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	0.4
Heat Deflection Temp.@ 264 psi,(F)	D 648	187
Haze ,%	D1003	0.6

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.