



SAN900

SAN900 offers a balance of chemical resistance and physical properties with high transparency.

Physical Property	ASTM Test Method	Typical Value
Melt Flow (g/10 min.)	D 1238	8.5
Specific Gravity	D 792	1.07
Tensile Strength, @ Yield (psi)	D 638	9600
Elongation @ Break(%)	D 638	2.1
Flexural Modulus, (psi)	D 790	541000
Notched Izod Impact @ 73F,(ft-lb/in)	D 256	0.3
Heat Deflection Temp.@ 264 psi,(F)	D 648	184
Haze ,%	D1003	0.6

To the best of our knowledge the information contained herein is accurate. However, Neither Chemical Resources, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for use contemplated, manner of use and whether there is any infringements of patents is the sole responsibility of the user. The above information gives typical properties only and is not to be used for specification purposes.